

T-Rex Power Fast Grab

Revision: 14/09/2018

Page 1 from 3

Technical data

Basis	MS Polymer
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (23°C/50% R.H.)	Ca. 5 min
Curing speed * (23°C/50% R.H.)	Ca. 2 mm/24h
Hardness**	65 ± 5 Shore A
Density**	1,47 g/ml
Maximum allowed distortion	± 20 %
Max. tension (ISO 37)**	3,20 N/mm ²
Elasticity modulus 100% (ISO 37)**	2,10 N/mm ²
Elongation at break (ISO 37)**	300 %
Temperature resistance**	-40 °C → 90 °C
Application temperature	5 °C → 35 °C

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

T-Rex Power Fast Grab is a high quality, neutral, elastic, 1-component adhesive sealant based on MS-Polymer with a very high initial tack.

Properties

- High initial tack reducing the need for initial support.
- Fast curing
- Good extrudability
- high shear strength after full cure (no primer)
- Stays elastic after curing and very sustainable
- No odour.
- Can be painted with water based systems
- Good weather and UV resistance
- Does not contain isocyanates and no silicones
- Good adhesion on slightly moist substrates

Applications

- Sealing and bonding in the building and construction industry.
- Elastic bonding of panels, profiles and other pieces on the most common substrates (wood, MDF, chipboard, etc).

- Elastic structural bonding in car and container industry.

Packaging

Colour: white, black, grey, silver grey, sandstone, other colors on request

Packaging: 290 ml cartridge, other packaging on request

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

Chemical resistance

Good resistance to (salt)water, aliphatic solvents, hydrocarbons, ketones, esters, alcohols, diluted mineral acids and alkalis. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

T-Rex Power Fast Grab

Revision: 14/09/2018

Page 2 from 3

Substrates

Substrates: all usual building substrates, treated wood, PVC, plastics, ...

Nature: rigid, clean, dry, free of dust and grease.

Surface preparation: Porous surfaces in water loaded applications should be primed with Primer 150. Prepare non-porous surfaces with Soudal primer or cleaner (see Technical Data Sheet).

T-Rex Power Fast Grab is has been tested on following metal surfaces: AlCuMg1, AlMg3, AlMgSi1, stainless steel, electro-galvanized steel, steel ST1403, hot dip galvanized steel.

T-Rex Power Fast Grab also has a good adhesion on plastics: polystyrene, polycarbonate (Makrolon®), PVC, polyamide, fiberglass reinforced epoxy, polyester. While producing plastics very often releasing agents, processing aids and other protective agents (like protection foil) are used. These should be removed prior to bonding or sealing. For optimum adhesion the use of Surface Activator is recommended. We recommend a preliminary adhesion test on every surface. NOTICE: bonding plastics like PMMA (e.g. Plexi® glass), polycarbonate (e.g. Makrolon® or Lexan®) in stress loaded applications can give rise to stress cracking and crazing in these substrates. The use of T-Rex Power Fast Grab is not recommended in these applications. Not suitable for PE, PP, PTFE (eg Teflon®), bituminous substrates, copper or copper-containing materials such as bronze and brass. We recommend a preliminary adhesion and compatibility test on every surface.

Joint dimensions

The optimal bond thickness for this product is at least 2 mm for the elastic properties to come to full justice.

Application method

Application method: With manual- or pneumatic caulking gun.

Cleaning: Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing).

Finishing: With a soapy solution or Soudal Finishing Solution before skinning.

Repair: With the same material

Health- and Safety Recommendations

Take the usual labour hygiene into account.

Consult label and material safety data sheet for more information.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

T-Rex Power Fast Grab

Revision: 14/09/2018

Page 3 from 3

Remarks

- T-Rex Power Fast Grab may be overpainted with water based paints, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application.
- The drying time of alkyd resin based paints may increase.
- T-Rex Power Fast Grab can be applied to a wide variety of substrates. Due to the fact that specific substrates such as plastics, like polycarbonate, etc, may differ from manufacturer to manufacturer, we recommend preliminary compatibility test.
- While producing plastics very often releasing agents, processing aids and other protective agents (like protection foil) are used. These should be removed prior to bonding. For optimum adhesion the use of Surface Activator is recommended.
- T-Rex Power Fast Grab can not be used as a glazing sealant.
- T-Rex Power Fast Grab can be used for bonding of natural stone, but it cannot be used as a joint sealant on this type of surface. T-Rex Power Fast Grab can therefore only be used on the bottom of natural stone tiles.
- When applying, make sure that the surface of the materials is not smudged with sealant.
- A total absence of UV can cause a color change of the sealant.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.
- Not suitable for bonding aquariums.
- Do not use in applications where continuous water immersion is possible.
- Discoloration due to chemicals, high temperatures, UV-radiation may occur. A change in color does not affect the technical properties of the product.

- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discolouration and loss of adhesion.

Environmental clauses*Leed regulation:*

T-Rex Power Fast Grab conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.